



TJ7603

Product Features:

- 13.5-oz, 100% polyester with mechanical stretch bonded with 100% polyester micro fleece
- 1000mm/1000g/m² waterproof/breathability rating
- Double needle topstitching throughout

Adult tall sizes: LT-4XLT

Icons/Fabric Features:



Available Colours and PMS Colours

Textile fabric colours are subject to dye lot variation and will not be exact match to print pantone reference



Due to the nature of polyester, special care must be taken throughout the decoration process.

TJ7603 - COAL HARBOUR® Everyday Soft Shell Tall Jacket

GARMENT MEASUREMENTS					
Size	LT	XLT	2XLT	3XLT	4XLT
Chest - <i>Half Measure</i>	24 1/2"	26"	27 1/2"	29 1/2"	31 1/2"
Chest - <i>Full Measure</i>	49"	52"	55"	59"	63"
Body Length from HPS	32"	33"	34"	34 1/2"	35"
Sleeve Length from CB	38 1/4"	39 1/4"	40"	40 3/4"	41 1/2"

Finished measurements in inches. Refer to "How to Measure" guide for detailed information on measurement instructions.

ADULT - TALL General Sizing Guide					
Size	L	XL	2XL	3XL	4XL
Chest	42"-44"	46"-48"	50"-52"	54"-55"	56"-57"
Waist	35"-38"	38"-41"	41"-44"	44"-47"	47"-50"
Sleeve Length REGULAR - CB	35"-36"	36"-37"	37"-38"	38"-39"	38 1/2"-39"
Sleeve Length TALL - CB	37"-37 1/2"	38"-38 1/2"	39"-39 1/2"	40"-40 1/2"	40 1/2"-41"

COAL HARBOUR®

PRINTING INSTRUCTIONS FOR POLYESTER FABRICS

Due to the nature of 100% polyester, special care must be taken throughout the printing process. Here are some tips to effectively decorate our performance products.

- Garment temperature must not exceed 320°F or 160°C. Exceeding this temperature will cause the fabric to shrink, become wavy or cause dye migration.
- Dryer temperature and belt speeds must be changed accordingly for polyester fabric.
- If flashing these garments, do not exceed 1-2 seconds. Anything longer may damage the fabric as stated above.
- **Screen Printing:** These garments require the use of poly inks that cure at a lower temperature. A Dyno Grey base blocker on all colours and a second white base blocker on all dark colours are recommended. Please consult your ink supplier for more information.
- Polyester requires a longer cooling time than cotton. Avoid overlap of garments and screen-print/heat transfer until the garments are cooled. Failure to cool the fabric prior to stacking into a printer's fold may cause the fabric and applied ink to stick together.
- **Heat Transfers:** Poly mark heat transfers need to be created with an anti-migration layer in the design. This process can only be done on white or very light coloured fabric. Inks used in printing paper design need to be darker than the base fabric or colour will migrate with the fabric colour resulting in a bleeding effect.
- **Sublimation Printing:** As noted for the poly mark heat transfers, this process can only be done on white or very light coloured fabric. Inks used in printing paper design need to be darker than the base fabric or colour will migrate with the fabric colour resulting in a bleeding effect.
- If you heat press these garments, you must adjust the time, temperature and pressure. Failure to do so may damage the fabric as stated above.
- A test sample run is recommended, especially if you have a large order or if your printer does not specialize in printing on performance fabrics.